

DARACLEAN[®] 259 AQUEOUS CLEANING SOLUTION

GENERAL DESCRIPTION

DARACLEAN[®] 259 is a low-foaming, all-purpose cleaning solution designed for use on a broad spectrum of soils.

COMPOSITION

DARACLEAN[®] 259 is formulated with a blend of surfactants, corrosion inhibitors, and phosphates. It is safe for use with glass, ceramics, plastics, and metal.

SOIL REJECTING PROPERTIES

DARACLEAN[®] 259 possesses excellent soil-rejecting qualities. After soils are lifted from part surfaces they are suspended in the cleaner for a short time. Over time, solids will settle out, and oil and grease droplets will coalesce and float on the surface of the solution. Removal of soils can easily be accomplished using filters or skimmers as necessary. This action extends the useful life of DARACLEAN[®] 259 much further than emulsion-type cleaning solutions.

APPLICATION METHOD

DARACLEAN[®] 259 is designed to for use with immersion, spray, and ultrasonic applications.

Cleaning Method	Concentration	Temperature	Typical Duration
Immersion	5 - 30%	80° - 180°F (27 - 82°C)	0.5 - 30 Minutes
Ultrasonic	5 - 30%	80° - 180°F (27 - 82°C)	0.5 - 30 Minutes
Spray	3 - 20%	130 - 180°F (54 - 82°C)	0.25 - 3 Minutes
Steam	3 - 20%	150 - 200°F (66 - 93°C)	1 - 5 Minutes

Operating parameters should be optimized for each individual application.

INDUSTRIAL STRENGTH

DARACLEAN[®] 259 has proven ability at removing machine oils, lube oils, cutting fluids, buffing compounds, and even tough, carbonized soils. Using aggressive alkaline chemistry, heavy petroleum-based oils and carbonized soils are broken down and pulled free from part surfaces.

PACKAGING

55 Gallon Drum (208 Liters) Part Number: 01-6160-45

DARACLEAN® 259 PROPERTIES

pH Level	13-14	Caustic	Higher pH cleaners are more aggressive and will clean tougher soils but high pH levels can also corrode or etch soft metal surfaces.
	11 - 13	High Alkaline	
	9 - 11	Alkaline	
	7 - 9	Neutral	
Foam Level	High		High foam levels will penetrate cracks and holes better but foam cannot be tolerated in spray applications.
	Moderate		
	Low		
Silicates	Yes	No	Silicates prevent corrosion of metal surfaces but can form mineral films at high temperatures.
Phosphates	Yes	No	Phosphates provide excellent cleaning action but are subject to environmental regulations.
Hard Water tolerance	High		Hard water can suppress cleaning actions. Some cleaners are formulated to counteract hard water effects.
	Moderate		
	Low		
Aerospace Compliant	Yes	No	See Specification Compliance.
SCAQMD Certified	Yes	No	VOC (10%) 0.0 g/L.

 Correct Application

CONCENTRATION VERIFICATION

HACH Alkalinity Titration Kit*

Titration	0.5N Sulfuric Acid
Indicator	Bromcresol Green-Methyl Red
Concentration %	Titration drops × 0.65

* Ordering info: **Alkalinity Test Kit, Model AL-TA; Product # 2314500; Mfr. Hach Company; Website www.hach.com**

DARACLEAN® 259 APPLICATIONS

Excellent	••••	Aluminum	Anodized Aluminum	Brass & Bronze	Carbon Steel & Cast Iron	Copper	Magnesium	Nickel & Superalloys	Plating (Cd, Cr, Ir, Pt)	Stainless Steel	Titanium	Zinc
Good	•••											
Fair	••											
Poor	•											
Not Recommended												
Water-Soluble Oils	•••	••	•••	•••	•••	••	••••	•••	••••	••••	••••	••••
Machining Fluid	•••	••	•••	•••	•••	••	••••	•••	••••	••••	••••	••••
Synthetic Coolants	•••	••	•••	•••	•••	••	••••	•••	••••	••••	••••	••••
Medium Weight Oils	•••	••	•••	•••	•••	••	••••	•••	••••	••••	••••	••••
Lube Oils	•••	••	•••	•••	•••	••	••••	•••	••••	••••	••••	••••
Buffing Compounds	•••	••	•••	•••	•••	••	••••	•••	••••	••••	••••	••••
Motor Oils	•••	••	•••	•••	•••	••	••••	•••	••••	••••	••••	••••
Heavy Petroleum Oils	•••	••	•••	•••	•••	••	••••	•••	••••	••••	••••	••••
Carbonized Soils	•••	••	•••	•••	•••	••	•••	•••	•••	•••	•••	•••
Railroad & Axle Grease	•	•	•	•	•	•	••	•	••	••	••	••
Glues												
Spray Adhesives												



NFPA Rating (Concentrate)